

RUSSTECH MORTARPEL-S

*SUPERIOR INTEGRAL
WATER REPELLANT
ADMIXTURE FOR CONCRETE
MASONRY MORTAR*

DESCRIPTION:

RUSSTECH MORTARPEL-S is a unique multi-component, liquid water repellent admixture based on a new technology that exhibits superior performance versus conventional water repellents. When introduced into the mortar, **RUSSTECH MORTARPEL-S** provides long-lasting resistance to water penetration by reacting to form a very effective water repellent network throughout the masonry mortar. Polymeric admixtures are a proven technology and have earned a reputation for its ability to effectively prevent moisture from penetrating concrete masonry walls and masonry mortar.

RUSSTECH MORTARPEL-S, when incorporated properly in concrete masonry mortar as part of a **RUSSTECH WATERPEL-S** masonry block system, will provide superior water repellency performance based on NCMA TEK 19, spray bar test and ASTM E514 wind driven rain test.

APPLICATIONS:

RUSSTECH MORTARPEL-S is an integral water-repellant admixture system for use in:

- Masonry Mortar

ADVANTAGES:

- Less maintenance and moisture damage due to permanent water repellency
- Less penetration at the surface reduces coats of paint required
- Improves color trueness and consistency
- Reduces mildew and mold growth
- Enhances texture
- Controls and reduces efflorescence

DOSAGE RATE:

RUSSTECH MORTARPEL-S is recommended for use in masonry mortar at 4 fluid ounces (118 mL) with each bag or cubic foot of cementitious materials incorporated into the masonry mortar mix. For each bag of pre-blended masonry cement, use 4 fluid ounces (118 mL).

PRECAUTIONS:

RUSSTECH MORTARPEL-S will not correct building design flaws, out of spec materials, mix proportion errors, incorrect manufacturing procedures, or unorthodox construction practices. Proper manufacturing procedures, mixing, and proportioning of masonry mortar mixes must be incorporated. **RUSSTECH** cannot be responsible for incorrect use of

RUSSTECH MORTARPEL-S.

Rake joints are not permitted. Be sure to cover the top courses at the end of each workday to prevent collection of water in cores. If necessary, only use mild acid for cleanup. Do not use high pressure cleaning methods.

TECHNICAL NOTE:

Flashing and weep hole design details are available upon request.

Efflorescence occurs when excess calcium salts become soluble again from moisture in the environment around the masonry unit. External sources of moisture can be humidity, rainfall, condensation, or snow etc. When these salts become soluble, they migrate to the surface during the evaporation process, consequently, staining the surface. **RUSSTECH MORTARPEL-S**, as mentioned earlier, effectively reduces moisture from penetrating the masonry surface and may be helpful in stopping salts from becoming soluble and migrating to the surface. It is important to point out though, that the addition of **RUSSTECH MORTARPEL-S** alone, will not guarantee the control of efflorescence.

RUSSTECH cannot be responsible for incorrect use of **RUSSTECH MORTARPEL-S**.

RUSSTECH MORTARPEL-S MORTAR ADMIXTURE *must* be incorporated in the masonry mortar in conjunction with the integral water repellent admixture for concrete block to ensure a permanent moisture-repellant wall system.

STORAGE:

RUSSTECH MORTARPEL-S may freeze at temperatures below 40 F (4 C). Freezing will harm this material, so, precautions should be taken to protect it from freezing. If it should freeze, it will no longer be effective as a water repellent in the masonry mortar.

DISCARD PRODUCT THAT HAS FROZEN OR HAS BEEN EXPOSED TO FREEZING TEMPERATURES. IT WILL NO LONGER BE EFFECTIVE!

RUSSTECH MORTARPEL-S should be stored in sealed containers where temperatures don't exceed 118 F (48 C).

INSTRUCTIONS:

Masonry mortar materials should be mixed according to ASTM C 270 and the directions listed below:

1. Thoroughly mix all mortar materials and water until consistency is drier than normal.
2. Introduce **RUSSTECH MORTARPEL-S** into the mix at the correct dosage rate.
3. While continuing to mix, add water to the mixture until desired consistency is reached. Make sure mortar mixes for a total of 4-5 minutes.
4. After final mixing, mortar should be placed within 2-1/2 hours. During this time, the mortar can be retempered if needed.

Correct mortar joint tooling is critical to water repellency of the joint. According to the National Concrete Masonry Association (NCMA), concave-tooled joints ensure the best water repellency performance. It is recommended that when **RUSSTECH MORTARPEL-S** is used in the mortar that all joints be tooled concave.

PACKAGING:

RUSSTECH MORTARPEL-S is available in 8 fluid ounce (236 mL) bottles and packaged 12 bottles per case for masonry mortar.

SHELF LIFE:

12 months

VISIT US ON THE WEB AT:

www.RussTechnet.com



RussTech Inc.

"We Add The Difference"